

ELASTOSIL® N 179 black

RTV-1 Silicone Adhesive / Sealant

Characteristics

ELASTOSIL® N 179 black is a non-slump, one-part silicone rubber that cures at room temperature under the influence of atmospheric moisture.

Special characteristics

- Neutral-curing system (alkoxy)
- Non-slump
- Good resistance to mineral oil and coolant fluids
- Primerless adhesion to many substrates

Application

- Multipurpose adhesive for technical applications
- FIPG and CIPG applications

Processing

ELASTOSIL® N 179 black is a one-part room temperature vulcanizing sealant that cures to a flexible silicone rubber on exposure to water vapor in the air. During the curing process a small amount of an alcohol is released. The crosslinking starts at all places where

the paste comes into contact with atmospheric moisture and proceeds from the outer to the inner parts of the silicone. After about 25 minutes a skin of cured material is formed at the surface. After formation of a sufficiently thick skin, glued parts may be handled without destruction.

For the crosslinking to take place, water vapor from the air is necessary. For this reason the curing rate strongly depends on the atmospheric humidity in the surrounding. The higher the atmospheric moisture the faster the material will be cured fully. The temperature has a great influence on the curing rate as well. The higher the temperature the faster the material will be fully cured.

If removing of silicone rubber from machines or dispensing equipment is necessary, white spirit is recommended as a solvent. However, cleaning should take place before the rubber is fully cured. Afterwards only the use of mechanical forces in combination with a swelling solvent or the use of high temperatures of approximately 100 °C will help to remove sealant residues.

ELASTOSIL® N 179 black shows good primerless adhesion to many substrates. We recommend running preliminary tests to optimize conditions for the particular application.

Product data (uncured)

Property	Test method	Unit	Value
Color			Black
Density at 23 °C		[g/cm ³]	1.25
Extrusion rate, 3-mm nozzle, pressure 0.21 N/mm ² , 23 °C		[g/10s]	3
Skin-forming time, 23 °C / 50 % RH		[min]	25
Curing time, 23 °C / 50 % RH		[h/mm]	24

These figures are only intended as a guide and should not be used in preparing specifications.

Product data (cured)

Property	Test method	Unit	Value
Color			Black
Density at 23 °C	ISO 2781	[g/cm ³]	1.27
Hardness Shore A	ISO 868		45
Elongation at break	ISO 37	[%]	500
Tensile strength	ISO 37	[N/mm ²]	3.0

2 mm, 14 d storage at 23 °C / 50 % RH.

These figures are only intended as a guide and should not be used in preparing specifications.

Advice on use of this material as FIPG or CIPG sealant is given in our leaflet "Modern Sealing Techniques with Silicone Rubber", comprehensive instructions are given in our leaflet "ELASTOSIL® RTV-1 Silicone Rubber."

Storage

ELASTOSIL® N 179 black has a shelf life of at least 9 months when stored between 5 °C and 25 °C in the originally sealed container. The 'Best use before end' date of each batch appears on the product label.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety information

During vulcanization of ELASTOSIL® N 179 black a total of 4 % by weight of an alcohol is released. These vapours should not be inhaled for long periods or in high concentration. Hence good ventilation of the works place is necessary.

Detailed safety information is contained in each Material Safety Data Sheet, which can be obtained from our sales offices.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001. The Business Unit Elastomers of the Division Silicones is ISO/TS 16949 certified.

WACKER

and ELASTOSIL® are registered trademarks of Wacker-Chemie GmbH.

Version 3.00 from 13-02-04 replaces Version 2.00 from 20-08-03

For technical, quality, or product safety questions, please contact:

Wacker-Chemie GmbH
WACKER-SILICONES
Hanns-Seidel-Platz 4
D-81737 Munich, Germany

Silicone-Info Service
Germany:
Tel.: 0-800-6279-800
International:
Phone: +800-6279-8000

www.wacker.com
silicones@wacker.com